

Type	MP	AV	Colour	Viscosity		Solubility					Remarks	Summary 5	02.12	
	Kofler 6 min°C			Gardner	4 DIN 53214	mPas	AR	AL	E	A				W
3100		5	8	7500	75% Eac	20°C	+	-	+	+	-	flexible, good adhesion, PI+L on metal, films+plastics		
3115		8	8	2250	75% Eac	20°C	+	o	+	+	-	like 3100, high flexible, TAA reduction		
3200		10	8	9000	70% 6/9	20°C	+	+	+	o	-	offset, hydrophobic, water balance, adhesion+gloss		
4100	130±10	135	9	400	55% Eac/Et	20°C	-	-	o	+	nN	hard resin with excellent adhesion+resistance		
VP 3337		5	8	7500	75% I-H	20°C	+	+	+	o	-	flexible, aliphatic soluble adhesion promoter, L+PI		
VP 3379		10	9	10000	100%	50°C	+	-	+	+	-	solvent free adhesion promoter, L+PI		
VP 3979		5	8	1500	70% Buac	20°C	+	-	+	o	-	flexible, good adhesion, L, primer, key coat		
VP 4696		65	8	8000	80% EtOH	20°C	+	-	+	o	nN	adhesion resin for "ester free" systems, pen inks		
VP 5314	150±10	2	5	2000	60% Eac	20°C	-	-	o	+	-	hard resin, pale, saponification stable, PVB compatible, PI		
VP 5342		3	1	2250	70% Eac	20°C	o	-	+	+	-	pale, high flexible adhesion promoter, PVB compatible		
VP 5358		10	5	1500	60% I-H	20°C	+	+	+	-	-	soya alkyd, 63% oil, wood lacquers, water proof		
VP 5426		1	2	2000	75% Eac	20°C	o	-	+	+	-	adhesion resin, NC+PVB-compatible, PI+L		
VP 5811		2	3	11500	100%	40°C	+	-	+	+	e	flexible adhesion promoter, emulsifiable, L+PI+AD		

AR - aromatics AL - aliphatics E - ester A - alcohol W - water

Eac - ethyl acetate Et - ethanol I-H - Isopar H w.sp. - white spirit K-30 Buac - butyl acetate 6/9 - PKWF 6/9 PI - printing inks L - lacquers AD - adhesives

+ soluble - insoluble o limited soluble nN after neutralisation e emulsifiable